

AITIOU

AIC-B302020(C-02)

⊙ Amorphous Toroidal Core (Used Inductore):

⊙ Mechanical Properties:

Bare Core Dimensions (mm)			Finished Core Dimensions (mm)			Coating Material & Color
O.D _{MAX}	I.D _{MIN}	H.T _{±0.2}	O.D _{MAX}	I.D _{MIN}	H.T _{MAX}	
3.0	2.0	2.0	3.5	1.8	2.5	Blue

⊙ Typical Parameters and Magnetic Properties:

Lm (mm)	Ac (mm ²)	Wa (mm ²)	WaAc (mm ⁴)	Vol (mm ³)	100KHz, 80A/m RT	
					Φ _c (μ Wb)	B _s
7.85	0.8	2.54	2.03	7.85	0.88	0.55


⊙ Core Finished Material:

Insulating Covers:UL94V-0 or equivalent

⊙ Temperature Range:

Storage temperature-20 ~ +50°C Ambient Temperature

Operating Temperature -40 ~ +120°C Case Surface Temperature



WIRE	0.2Φ	TURNS	1 Ts	TEMP.	25°C
------	------	-------	------	-------	------

2 TEST INSTRUMENTS: ZENTECH 3302 LCZ (uH)

The inductance attenuation curve

