

# AITIOU

## A1616C

⊙ Amorphous Toroidal Core(Used Common-Mode Choke )

⊙ Mechanical Properties:

Bare Core Dimensions (mm)			Finished Core Dimensions (mm)			Coating Material & Color
od $\pm 0.3$	id $\pm 0.3$	h $\pm 0.3$	OD $\pm 0.3$	ID $\pm 0.3$	H $\pm 0.3$	
16.0	10.0	8.0	17.8	8.5	9.8	White

⊙ Typical Parameters and Magnetic Properties:

Lm (mm)	Ac (mm <sup>2</sup> )	Wa (mm <sup>2</sup> )	WaAc (mm <sup>4</sup> )	Vol (mm <sup>3</sup> )	Bs@25°C (T)	$\mu_i$ 10KHz	A <sub>L</sub> @10KHz ( $\mu$ H)
40.82	19.20	56.72	1088.95	979.68	1.10	60000.00	35MIN


⊙ Core Finished Material:

Insulating Covers:UL94V-0 or equivalent

⊙ Temperature Range:

Storage temperature-20 ~ +50°C Ambient Temperature

Operating Temperature -40 ~ +120°C Case Surface Temperature



WIRE	0.5 $\phi$	TURNS	1.0 Ts	TEMP.	25°C
------	------------	-------	--------	-------	------

TEST INSTRUMENTS: ZENTECH 3302 LCZ

The inductance attenuation curve

