

AITIOU

A2016C

⊙ Amorphous Toroidal Core(Used Common-Mode Choke)

⊙ Mechanical Properties:

Bare Core Dimensions (mm)			Finished Core Dimensions (mm)			Case Material & Color
od \pm 0.3	id \pm 0.3	h \pm 0.3	OD \pm 0.5	ID \pm 0.5	H \pm 0.5	
20.00	12.0	10.0	22.5	10.54	12.5	PBT or NY66, White

⊙ Typical Parameters and Magnetic Properties:

Lm (mm)	Ac (mm ²)	Wa (mm ²)	WaAc (mm ⁴)	Vol (mm ³)	Bs@25°C	μ_i 10KHz	A _L @10KHz (μ H)
					(T)		
50.24	32.00	87.21	2790.62	2009.60	1.10	60000	50 MIN


⊙ Core Finished Material:

Insulating Covers:UL94V-0 or equivalent

⊙ Temperature Range:

Storage temperature-20 ~ +50°C Ambient Temperature

Operating Temperature -40 ~ +120°C Case Surface Temperature



WIRE	0.5 ϕ	URNS	1.0 Ts	TEMP.	25°C
------	------------	------	--------	-------	------

TEST INSTRUMENTS: ZENTECH 3302 LCZ

The inductance attenuation curve

