

AITIOU

A2508C

⊙ Amorphous Toroidal Core(Used Common-Mode Choke)

⊙ Mechanical Properties:

Bare Core Dimensions (mm)			Finished Core Dimensions (mm)			Case Material & Color
od ± 0.3	id ± 0.3	h ± 0.3	OD ± 0.5	ID ± 0.5	H ± 0.5	
25.00	20.0	10.0	27.5	18.10	12.8	PBT or NY66, White

⊙ Typical Parameters and Magnetic Properties:

Lm (mm)	Ac (mm ²)	Wa (mm ²)	WaAc (mm ⁴)	Vol (mm ³)	Bs@25°C (T)	μ_i 10KHz	A _L @10KHz (μ H)
70.65	20.00	257.17	5143.48	1766.25	1.10	80000	23.0 Min


⊙ Core Finished Material:

Insulating Covers:UL94V-0 or equivalent

⊙ Temperature Range:

Storage temperature-20 ~ +50°C Ambient Temperature

Operating Temperature -40 ~ +120°C Case Surface Temperature



WIRE	0.5 ϕ	TURNS	1.0 Ts	TEMP.	25°C
------	------------	-------	--------	-------	------

TEST INSTRUMENTS: ZENTECH 3302 LCZ

The inductance attenuation curve

