

AITIOU

A1615E

⊙ Amorphous Toroidal Core

⊙ Mechanical Properties:

Bare Core Dimensions (mm)			Finished Core Dimensions (mm)			Coating Material & Color
O.D	I.D	H.T	O.D _{max}	I.D _{min}	H.T _{max}	
16.0	12.5	8.0	17.8	10.7	10.0	Grey

⊙ Typical Parameters and Magnetic Properties:

Lm (mm)	Ac (mm ²)	Wa (mm ²)	WaAc (mm ⁴)	Vol (mm ³)	100KHz, 80A/m RT		AL@10KHz (μH)
					ψc(μ·Wb)	Bs	
44.75	11.20	89.87	1006.60	626.43	24.64	1.10	14.0 MIN


⊙ Core Finished Material:

Insulating Covers:UL94V-0 or equivalent

⊙ Temperature Range:

Storage temperature-20 ~ +50°C Ambient Temperature

Operating Temperature -40 ~ +120°C Case Surface Temperature



WIRE	0.5¢	TURNS	9.5 Ts	TEMP.	25°C
------	------	-------	--------	-------	------

TEST INSTRUMENTS: ZENTECH 3302 LCZ

The inductance attenuation curve

